

Claims:

Please maintain the claims as follows:

Listing of Claims:

1-11 (Cancelled)

12. (Previously Presented) A carbon heating element comprising carbon acting as a good conductor and boron nitride acting as a conductivity-inhibiting material.

13. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon is obtained by firing organic substances.

14. (Previously Presented) A carbon heating element according to claim 12, further comprising carbon powder acting as a good conductor.

15. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element has a rectangular cross section.

16. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element is enclosed in a vessel filled with an inert gas.

17. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element has a specific resistance of about 4.5 to about $7.5 \times 10^{-3} \Omega \cdot \text{cm}$.

18. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element has a specific resistance of about $4.5 \times 10^{-3} \Omega \cdot \text{cm}$.

19. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element has a specific resistance of about $7.5 \times 10^{-3} \Omega \cdot \text{cm}$.

20. (Previously Presented) A carbon heating element according to claim 12, wherein the carbon heating element has a specific resistance of about $0.3 \times 10^{-3} \Omega \cdot \text{cm}$.
21. (Previously Presented) A carbon heating element according to claim 15, wherein the carbon heating element has a specific resistance of about 4.5 to about $7.5 \times 10^{-3} \Omega \cdot \text{cm}$.
22. (Previously Presented) A carbon heating element according to claim 15, wherein the carbon heating element has a specific resistance of about $4.5 \times 10^{-3} \Omega \cdot \text{cm}$.
23. (Previously Presented) A carbon heating element according to claim 15, wherein the carbon heating element has a specific resistance of about $7.5 \times 10^{-3} \Omega \cdot \text{cm}$.
24. (Previously Presented) A carbon heating element comprising carbon acting as a good conductor and a metal or a metalliod compound acting as a conductivity-inhibiting material, wherein the carbon heating element has a rectangular cross section.
25. (Previously Presented) A carbon heating element according to claim 24, wherein the carbon heating element is enclosed in a vessel filled with an inert gas.
26. (Previously Presented) A method of making a carbon heating element, comprising:
forming a carbon heating element comprising carbon acting as a good conductor and boron nitride acting as a conductivity-inhibiting material, wherein said carbon is obtained by firing organic substances.
27. (Previously Presented) A method of making a carbon heating element according to claim 26, wherein the organic substances yield carbonization of at least 5% after firing.

28. (Previously Presented) A method of making a carbon heating element according to claim 26, wherein the organic substances comprise polyvinyl chloride and furan resin.